

Tribol GR 4747/220-2 HT

High-temperature grease

Description

CASTROL TRIBOL™ GR 4747/220-2 HT (previously named Tribol™ 4747/220-2) high-temperature grease with TGOA™ is a clear multi-service lubricant designed to extend the service life of bearings in heavy-duty applications and at elevated temperatures. The high base oil viscosity of CASTROL TRIBOL GR 4747/220-2 HT provides a heavier oil film for applications at slower speeds, higher loads and/or higher temperatures. The patented TGOA™ additive technology provides for an unsurpassed protection against friction and wear in the conditions above.

- CASTROL TRIBOL™ GR 4747/220-2 HT is formulated from a mixture of high-quality synthetic base oils (PAO & ester) and a lithium complex thickener.
- It contains corrosion inhibitors and antioxidants for long service life.
- The load carrying, antiwear and friction reducing capabilities of CASTROL TRIBOL GR 4747/220-2 HT exceed conventional complex greases. The high performance is the result of the TGOA additives which under relatively high specific loads and related temperatures, promote a non-destructive smoothing of the surface roughness in the micro-range.
- The smoothing effect leads to increases in actual load carrying areas and reduces friction.
- TGOA™ additives are very effective in protecting the machined surface of bearings during the critical “running-in” period.
- TGOA®’s additive package automatically reactivates to optimise lubrication and smooth rough surfaces when roughness peaks redevelop in shock load or stop-and-go operations. This is essential as good bearing surfaces mean bearing longevity.

Application

- CASTROL TRIBOL™ GR 4747/220-2 HT grease with TGOA™ is designed as a multi-service lubricant for heavy-duty applications of rolling and sliding bearings for temperatures up to 160°C (peak temperatures up to 180°C).
- CASTROL TRIBOL™ GR 4747/220-2 HT grease should be used when loads are moderate to heavy and speeds are slow to moderate.

Advantages

- CASTROL TRIBOL™ GR 4747/220-2 HT with TGOA™ offers increased load carrying capability due to higher viscosity base oils and surface smoothing as well as friction reducing properties of TGOA™.
- The lithium complex thickener is characterized by its excellent working and shear stability.
- Excellent thermal stability (dropping point >250 °C).
- The TGOA™ additives reduce wear at lowered operating temperatures as well as extended service life leading to decreased maintenance and repair costs.

Typical Characteristics

Name	Method	Units	Tribol GR 4747/220-2 HT
DIN Classification	DIN 51502	-	KP HC E 2 P -40
Thickener Type	-	-	Lithium complex
Worked Penetration	ASTM D217 / ISO 2137	0.1 mm	265 – 295
Dropping Point	ASTM D566 / ISO 2176	°C / °F	>250 / >482
Base Oil Viscosity @ 40°C / 104°F	ASTM D445 / ISO 3104	mm ² /s	220
Base Oil Viscosity @ 100°C / 212°F	ASTM D445 / ISO 3104	mm ² /s	25.4
Viscosity Index	ASTM D2270 / ISO 2909	-	146
Flash Point - open cup method	ASTM D92 / ISO 2592	°C / °F	280 / 536
Water Resistance	DIN 51807-1	Rating	0
Oxidation Stability - Rotating Pressure Vessel test (100h @ 99°C)	ASTM D942 / DIN 51808	pressure drop psi	<250
Oxidation Stability - Rotating Pressure Vessel test (300h @ 99°C)	ASTM D942 / DIN 51808	pressure drop psi	<400
Copper Corrosion (24 hrs, 100°C / 212°F)	ASTM D4048	Rating	2
Emcor Test	ASTM D6138 / ISO 11007 / DIN 51802	Rating	0/0
Four Ball Wear test - Wear Scar Diameter	DIN 51350-5E	mm	<0.7
SRV Test	DIN 51843-02-S	μ	<0.1
FAG-FE 9 test (A/1500/6000-150)	DIN 51821-02	-	Passed
Flow pressure @ -20°C	DIN 51805	mBar	225
Flow pressure @ -30°C	DIN 51805	mBar	340
Flow pressure @ -35°C	DIN 51805	mBar	450

1 mm²/s ^ 1cSt Subject to usual manufacturing tolerances

User Advice

- CASTROL TRIBOL™ GR 4747/220-2 HT grease with TGOA™ should not be mixed with greases using a different thickener.
- Lubricating intervals should be increased gradually after changing over to CASTROL TRIBOL™ GR 4747 to ensure complete removal of the previous lubricants and to use the TGOA™ additives to their full advantage. Their performance might be affected by residual greases containing solid lubricants!
- At peak temperatures of 180 °C relubrication intervals should be established by inspection.

Tribol GR 4747/220-2 HT

04 Sep 2015

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW
 Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719
www.castrol.com/industrial