



## Product Data

# Brayco Micronic 882

Hydraulic Fluid, Fire Resistant

## Description

Castrol Brayco™ Micronic 882 is a red colored synthetic hydrocarbon hydraulic fluid ISO viscosity Grade 15 for aircraft, ordnance, and industrial use. It contains no VI improvers and, unlike conventional hydraulic fluids, is not subject to polymer breakdown under high shear conditions. It can be used as a replacement and make-up oil for MIL-PRF-5606, and it is also compatible with MIL-PRF-6083 in all proportions. Brayco Micronic 882 has a high flash and fire point, exceptionally high auto ignition point, and very low flame propagation. Its properties also include controlled rubber swell for long seal life, low foaming, excellent anti-wear, and good corrosion and oxidation stability.

## Application

Brayco Micronic 882 is primarily designed as a fire resistant hydraulic fluid for aircraft and missile use, but also has many industrial applications where fire and fluid toxicity are a hazard. Brayco Micronic 882 is a direct replacement for MIL-PRF-5606.

## Characteristics

TEST METHOD	DESCRIPTION	MIL-PRF-83282D REQUIREMENTS	RESULT
D 4172	Lubricity, AWSD, mm		
	@ 1 kg load	0.21 Maximum	0.15
	@ 10 kg load	0.30 Maximum	0.25
	@ 40 kg load	0.65 Maximum	0.5
FTM 3009	Solid Particle Contamination per 100 mL		
	Autocount		
	5 - 15 Microns		
	15 - 25 Microns	10,000 Maximum	2500
	25- 50 Microns	1,000 Maximum	103
	50- 100 Microns	150 Maximum	32
D 4898(spec) FTM 3009 (spec)	100 + Microns	20 Maximum	5
		5 Maximum	0
	Gravimetric Residue, mg per 100 mL	0.3 Maximum	0.12
	Filtering Time, minutes	15 Maximum	9
D2270	Viscosity Index	---	129

Subject to usual manufacturing tolerances.

## Typical Physical Characteristics

TEST METHOD	DESCRIPTION	MIL-PRF-83282D REQUIREMENTS	RESULT
D 1298	API Gravity, degrees	---	36.5
Table 3	Specific Gravity @ 16/16°C (60/60°F)	Report	0.841
Table 8	Pounds per Gallon @ 16°C (60°F)	---	7.03
D 1298	Specific Gravity Variance	0.008 Maximum	0.001
D 445	Kinematic Viscosity, cSt		
	@ 205°C (400°F)	1.0 Minimum	1.1
	@ 100°C (212°F)	3.45 Minimum	3.57
	@ 40°C (104°F)	14.0 Minimum	14.6
	@ -40°C (-40°F)	2200 Maximum	2100
	@ -54°C (-65°F)		12,230
D 97	Pour Point, °C (°F)	-55 (-67) Maximum	-63 (-80)
D 92	Flash Point, COC, °C (°F)	205 (401) Minimum	224 (435)
D 92	Fire Point, COC, °C (°F)	245 (473) Minimum	250 (480)
D 664	Neutralization Number, mgKOH/g	0.10 Maximum	0.014
FTM 350	Evaporation Loss, % wt 6.5 hrs @ 205 °C (400°F)	20.0 Maximum	11.35
FTM 3458	Low Temperature Stability 72 hrs @ -40°C (-40°F)	No gelling, clouding, crystallization, solidification or separation	Pass
D 892	Foam, Sequence I		
	Tendency, ml	65 ml maximum	10
	Stability, ml	0	0
D 1744	Water by KFR, ppm	100 Maximum	41
FTM 352	Evaporation Effect on Wick Flammability	10 cycles Minimum	15

## Additional Information

Temperature Range Brayco Micronic 882 is designed to operate over the temperature range of -40°C to 205°C (-40°F to 401°F) Specification Brayco Micronic 882 meets all requirements and is qualified under military specification MIL-PRF-83282D, Amendment 1.

Brayco Micronic 882

14 Mar 2019

Castrol, the Castrol logo and related marks are trademarks of Castrol Limited, used under licence.

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either BP plc or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale. You should consult our local representative if you require any further information.

Castrol (UK) Limited, PO BOX 352, Chertsey Road, Sunbury On Thames, Middlesex, TW16 9AW  
Orders/Enquiries: 0345 9645111 Technical Enquiries: 0345 082 1719  
[www.castrol.com/industrial](http://www.castrol.com/industrial)